

# PROPERTIES

1. Product Name                      Chemical cross-linking  
    Closed Cell Rubber Foam  
    RUBAPELCA EP-151

2. Test Data

Testing Methods	Testing Items		Units	Values
JIS K 6767	Apparent Density		kg/m <sup>3</sup>	95
JIS K 6251	Tensile Strength		MPa	0.44
	Elongation		%	290
In reference to ASTM D 1056	Compression Strength	10%	kPa	25
		25%		40
		50%		110
	50% Compression Set	After 30min	%	62.7
		After 24hr		37.6
	JIS K 7312	C-type Hardness		—
JIS A 1412-2	Thermal Conductivity (at 0°C)		W/m · K	0.041

Note: The above values measured in our laboratory do not constitute a product specification.

3. Feature

Sulfur-free

October 1st, 2022  
 SANWA KAKO CO., LTD.  
 56 Butsugenji-cho, Kamitoba  
 Minami-ku, Kyoto City, Kyoto  
 601-8103 Japan  
 Tel: +81-75-671-5430